



# Leader Clipperlon 2120

## Modified PTFE Gaskets



### DESCRIPTION

Modified PTFE gasket material containing biaxial orientated chains to obtain a tight seal for demanding applications. Clipperlon 2120 is a very dense material with low compressibility, high recovery and low creep properties. Off-white in color and produced with Modified PTFE and barium sulfate filler.

### APPLICATION

Particularly suitable for use with hydrofluoric acid and a wide variety of different media across the whole pH-range. Applications can be found in chemical, pharmaceutical, food and beverage and general industry. Due to the high density this material is highly recommended for applications with monomers to avoid the 'popcorning' effect. This effect will be result when the monomer enters the micro-

voids of the PTFE.

### CHEMICAL COMPATIBILITY

Particularly suitable for use with hydrofluoric acid, but not pure hydrogen fluoride. Best for use with string alkalis, solvents, fuels, water, steam and chlorine. Other applications include solvents, fuels, water, oil, chlorine and caustics. A chemical resistance list is available upon request. Pressure up to 1200 psi Temperature from -450 F up to 500 F

### DELIVERY OPTIONS

Flange gaskets and sheets are available in thickness of 1/64", 1/32", 1/16", 1/8. Standard gaskets can be supplied in accordance with ASME B16.21, EN12560-1 as well as EN1514-1. Non-standard or special gaskets can be manufactured according to customer drawings, or by given sizes or Edrawing.

### TEMPERATURE

Particularly suitable for use with hydrofluoric acid, but not pure hydrogen fluoride. Best for use with string alkalis, solvents, fuels, water, steam and chlorine. Other applications include solvents, fuels, water, oil, chlorine and caustics. A chemical resistance list is available upon request. Pressure up to 1200 psi Temperature from -450 F up to 500 F

### SEALING CHARACTERISTICS

- non ageing
- significant reduced creep (non-cold flow)
- low leak rate
- good electrical insulation properties
- outstanding chemical resistance

## TECHNICAL DATA

max Temperature [°C]	260
min Temperature [°C]	-210
max Pressure [bar]	85
density [g/cm <sup>3</sup> ]	2.8
Leakage Specific Leak Rate [DIN 28090-2] [mg/(s*m)]	0.01
Minimum initial stress [DIN E 2505 part 2] [N/mm <sup>2</sup> ]	20
Maximum initial stress [DIN E 2505 part 2] [N/mm <sup>2</sup> ]	150
M-Value	3.5
Y- Value [psi]	2450
ASTM F36 Recovery [% min]	40
ROTT [Gb]	432
ROTT [a]	0.318

### LOCATIONS

905 W.13th Street DEER PARK, TX 77536, USA GLOBAL HEADQUARTERS

8622 South Choctaw Drive BATON ROUGE, LA, USA 70815

Purnovicka cesta 1026, 01401 BYTCA, Slovak Republic EUROPE HEADQUARTERS

### PHONE

+1 281 542 0600

+1 225 272 3126

+421 41 553 3853

### FAX

+1 281 542 5552

+225 272 3126

+421 41 553 2895

## TECHNICAL DATA

ROTT [Gs]

0.964

### LOCATIONS

905 W.13th Street DEER PARK, TX 77536, USA GLOBAL HEADQUARTERS

8622 South Choctaw Drive BATON ROUGE, LA, USA 70815

Pšurnovická cesta 1026, 01401 BYTCA, Slovak Republic EUROPE HEADQUARTERS

### PHONE

+1 281 542 0600

+1 225 272 3126

+421 41 553 3853

### FAX

+1 281 542 5552

+225 272 3126

+421 41 553 2895